



SILSPEC® 950 POLYMER CONCRETE

DESCRIPTION

SILSPEC® 950 POLYMER CONCRETE is a two-component rapid curing liquid polymer that cures to a dense, semi-flexible, weather, abrasion and impact resistant polymer mortar for the construction or repair of expansion and construction joints on parking and other structures. The combined polymer is mixed with SILSPEC® ENGINEERED AGGREGATE to form a polymer based mortar for joint nosing's or repairs. When installed with SILSPEC® RFS Reinforced Foam Seal it comprises the SSI PDX Joint System.

USES

- ◆ SILSPEC® 950, upon curing, develops a tough, chemical, wear, and impact resistant surface for use in areas exposed to foot and vehicular traffic. (Contact SSI for procedures for obtaining skid resistance)
- ◆ It is ideally suited for use as binder for mortar preparations.
- ◆ When combined with SILSPEC® ENGINEERED AGGREGATE, it can be used to repair damaged expansion and construction joints in parking and other structures. It can also be used for small repairs.
- ◆ Due to its low water absorption, it provides excellent protection during freeze-thaw cycles.
- ◆ When used in conjunction with SILSPEC® RFS Reinforced Foam Seal, it provides an alternative for strip seals, compression seals, T-Joints and elastomeric devices in new deck expansion joints.

PROPERTIES

Combined Liquid Components

Mixing Ratio	1:1 By Volume		
Viscosity	2,000 cps @ 77°F		
Color	Black		
Gel Time, minutes	15 minutes	60g Mass	
Elongation, percent	45 (7 Day)	ASTM D638#	
Tensile Strength, Min. PSI	2000 (7 Day)	ASTM D638#	
Shore D Hardness @ 25° C, (77° F.)	65-75	ASTM D2240	
Bond Strength		ASTM C882	
	2- Day Cure 2,000 psi		
	14- Day Cure 2,500 psi		
Compressive Properties		ASTM C882	
Compressive Strength	5,000 psi		
Compressive Modulus	90,000 psi		

Cured Mortar

Aggregate— Supplied by manufacturer

Compressive Strength	PSI @ 3 hrs. @ 24 hrs.	1,500 psi 5,000 psi	ASTM C579
Bond Strength	PSI	300	ASTM C882
Wet Bond Strength	PSI	450	Tex-618-J
Shrinkage on Cure	%	0.2	ASTM D2566
Resilience	%	95	Tex-618-J
Thermal Compatibility	—	Pass	ASTM C884
Water Absorption	% (24 hr.)	0.2	ASTM D570
Chloride Ion Permeability	Coulomb	0.0	AASHTO T277

Shelf Life— 2 years when stored properly in unopened containers.
Storage Conditions: Store at 40° F to 95° F
Condition at 65° F to 85° F before mixing.

PACKAGING & YIELD

Kit Yield	Components
0.5 cu ft (.014 cu m) Kit	Binder liquid & aggregate in 5 gallon pail

Kit can be mixed in the waterproof pail.

STANDARD TYPE

Will permit cure to a minimum of 7° C. (45° F.) SILSPEC® 900/950 Accelerator can be added to speed curing at low temperatures. Contact SSI for recommendations.

Modification in viscosity to decrease problems of sag or "running" on steep inclines or ramps can be made by adding additional aggregate. No modification of the material should be attempted without consulting SSI.

GENERAL USE PROCEDURES

Surface Preparation

Regardless of substrate, SILSPEC® 950 must be applied to clean, dry and sound surfaces for effective bond.

All unsound material must be removed from structurally sound substrate by jack hammering, sandblasting or similar mechanical methods.

All loose material must be removed by brushing, vacuuming or blowing. Old paint, rust or other coating must be removed by the proper methods.

Asphalt/Bituminous & Steel Substrates

Observe above methods carefully. Do not use solvents. NOTE: While SILSPEC® 950 adheres to asphalt, the asphalt itself has poor structural strength. Consequently, we recommend whenever possible, that SILSPEC® 950 be bonded to concrete or sound steel substrate.

Steel Surfaces shall be sandblasted to near white condition.

Mixing of Liquid Components

SILSPEC® 950 is a two-component product (Base and Reactor); these must be **thoroughly** combined prior to use in a separate container, in the proper ratio of one volume Base to one volume Reactor. **We strongly recommend that the cans be wiped out with a spatula (if this is not done, 10% or more of the material can be left in the container).** Therefore, it is critical that the material be scraped out of the cans in order to assure adequate liquid/aggregate ratio. In small batches only, Base and Reactor can be hand-mixed. However, mechanical mixing, using a heavy-duty low speed drill motor with paint-type paddle stirrers, is strongly recommended. Mixing time should not be less than three minutes. Care should be taken to ensure thorough mixing from top to bottom as well as the sides of the container.

CAUTION --- Water retards the cure of SILSPEC® 950 Polymer Concrete, therefore if a mixture of clean aggregate and water is used to clean the mixer, extreme care should be taken to ensure that the mixer is thoroughly dry and any uncured material is removed prior to mixing new material.

NOTE --- Do not mix more material than can be used at one time.

MIXING AND PLACING OF MORTAR

The mixed SILSPEC® 950 is made into a mortar by combining one (1) volume of mixed polymer with three and one half (3.5) volumes of SILSPEC® Engineered Aggregate.....cont.



SILSPEC® 950 POLYMER CONCRETE

After combining the base and reactor for a minimum of 3 minutes, it is placed in a mixing container, then add the SILSPEC®ENGINEERED AGGREGATE to produce a mortar. When mixing mortar in a bucket with a drill motor, never mix more than 1/2 CUFT at a time. Always measure the materials to insure the proper ratios. **Extreme care** should be taken to insure that the aggregate is mixed uniformly from top to bottom in the bucket. It is extremely important that the material be thoroughly compacted. Care should be taken to assure good compaction on the vertical face of the joint and along the side of the Styrofoam form. Simply smoothing the top with a steel float **is not** compacting the mix. A small margin trowel, or other means, should be used for compaction.

The blended batch must be applied to the surface in 5-10 minutes. Once spread out, working time will be approximately 1/2 hour depending upon temperature. Clean equipment immediately with Citrus Cleaner or other approved solvent.

When using SILSPEC® 950 as an expansion joint header, care should be taken to insure the mortar is even with the plane of the deck or a fraction lower. Leaving the mortar higher than the plane of the deck can subject it to snowplow or other impact damage. If after removal of the forming material the mortar is found to be higher than the adjacent deck or overlay, it may be re-profiled using a handheld grinder with a diamond cup wheel.

CURE

At 21°C. (70°F.) (surface & air temperature), the mortar will cure sufficiently to accept traffic in four hours. Higher temperatures will shorten the cure while lower temperatures will lengthen the cure time. For temperatures in excess of 38°C. (100°F.), or lower than 15°C. (60°F.), contact S.S.I. for recommended procedures and cure time.

In cold weather, we recommend that liquid and aggregate be stored in a heated area until just prior to use.

Temperature	Working Time	Initial Cure Time*
50°F	40 min	12 hrs
60°F	30 min	8 hrs
70°F	25 min	4 hrs
80°F	20 min	3 hrs
90°F	15 min	2 hrs
100°F	10 min	1.5 hrs

* Compressive Strength reaches approximately 1000 psi.

CAUTION

- ◆ During all operations, established safety codes and workman protection must be observed.
- ◆ Use of protective creams, clothing, goggles, and rubber gloves are recommended during all phases of handling and use. Read and follow all handling precautions on labels. Use common sense in handling SILSPEC® 900PNS and all other chemicals.
- ◆ Observe good housekeeping rules and regulations during all phases of use and handling of either unmixed or mixed product.
- ◆ Ample ventilation should be provided during all periods of sandblasting, mixing and application procedures.
- ◆ In accordance with ICC Regulation #49, Item 173.4: Containers containing less than one (1) fluid ounce of liquid are considered non-hazardous material. Empty containers may be crushed and should be disposed of in accordance with state and local regulations.
- ◆ Remove epoxy immediately with clean, dry towel and wash skin thoroughly with soap and water.
- ◆ Good housekeeping rules are always important. Provide ample ventilation in all areas of handling, mixing and use. Avoid prolonged breathing of possible fumes. Minimize skin contact. Use of goggles, rubber gloves and skin creams is recommended. If material gets into eyes, flush thoroughly with clean water for 20 minutes; then seek medical treatment. Observe all safety precautions when using any type of solvent for cleaning tools or equipment.

CLEAN UP

All tools, other application or mixing equipment must be cleaned at frequent intervals and while SILSPEC® 950 remains soft and uncured.

For cleaning hand tools, CITRUS CLEANER or other approved solvents are most effective, or cleaning can be accomplished using waterless hand cleaner.

*NOTE --- Some solvents are **FLAMMABLE** and all safety codes and regulations governing their use must be observed.*

MATERIAL SPILL

Collect with absorbent material. Dispose of in accordance with local, state and federal disposal regulations.

FOR CHEMICAL EMERGENCY CALL
1-800-842-9300
24 hours per day, 7 days per week.

CONTACT

Contact SSI for further information or installation instructions. It is the users responsibility to familiarize themselves with all safety precautions prior to use. A product SDS is provided upon request by contacting SSI at **(800)888-8909**.

Warranty Limitations: SSI REPRESENTS TO THE PURCHASER OF THIS PRODUCT FROM SSI (REFERRED TO AS CUSTOMER) THAT THE INFORMATION IN THIS LITERATURE IS AN ACCURATE DESCRIPTION OF THE TYPICAL CHARACTERISTICS, PROPERTIES AND USES OF THE PRODUCT, IF TRANSPORTED, STORED AND APPLIED IN ACCORDANCE WITH THIS LITERATURE AND THE REFERENCED MATERIAL SAFETY DATA SHEET. UNLESS SSI PROVIDES BEFORE PRODUCT INSTALLATION AN EXPRESS WRITTEN WARRANTY AFTER RECEIPT AND EVALUATION OF SPECIFIC WRITTEN PROJECT CONDITIONS AND APPLICABLE SCOPE DOCUMENTATION, SSI'S EXCLUSIVE WARRANTY IS THAT THE PRODUCT WILL CONFORM TO THE SALES REPRESENTATIONS STATED HEREIN AND THE CURRENT MATERIAL SAFETY DATA SHEET. SSI EXPRESSLY DISCLAIMS ALL OTHER EXPRESS OR IMPLIED WARRANTIES, INCLUDING WITHOUT LIMITATION WARRANTIES OF MERCHANTABILITY AND FITNESS FOR PARTICULAR PURPOSE. IN NO EVENT SHALL SSI'S LIABILITY FOR DAMAGES ARISING FROM THE SALE OF THIS PRODUCT THE AMOUNT OF PURCHASE PRICE RECEIVED BY SSI FROM CUSTOMER FOR THIS PRODUCT DELIVERED TO THE PROJECT IN QUESTION, OR AT SSI'S SOLE OPTION, SSI MAY REPLACE THE PRODUCT OR PORTION THEREOF THAT DOES NOT CONFORM TO THE FOREGOING REPRESENTATION. SSI EXPRESSLY EXCLUDES ANY LIABILITY FOR SPECIAL OR CONSEQUENTIAL DAMAGES.

CUSTOMER IS SOLELY RESPONSIBLE FOR EVALUATING JOB CONDITIONS AND THE SUITABILITY OF DESCRIBED PHYSICAL PROPERTIES AND CHARACTERISTICS OF THE PRODUCT TO MEET SPECIFIED OR APPARENT PROJECT REQUIREMENTS AND FOR APPLICATION OF THE PRODUCT IN ACCORDANCE WITH SSI'S RECOMMENDATIONS.

THESE REPRESENTATIONS ARE INTENDED FOR RELIANCE EXCLUSIVELY BY THE CUSTOMER AND ARE NOT INTENDED TO BENEFIT ANY OTHER PERSON OR ENTITY. THESE EXCLUSIONS, MODIFICATIONS OR LIMITATIONS OF WARRANTIES, INCLUDING THEIR EFFECT ON RIGHTS AND REMEDIES, THAT ARE EFFECTIVE AGAINST ARE ALSO EFFECTIVE AGAINST SUBSEQUENT PURCHASERS, USERS AND THIRD PARTY BENEFICIARIES OF THE SALE OF THIS PRODUCT.

SSI UNDERTAKES NO RESPONSIBILITY FOR STORAGE, MIXTURE, PREPARATION OF SURFACES, APPLICATION, USE OR MIS-USE OF PRODUCT OR ITS CONFORMITY TO SPECIFICATIONS THAT ARE NOT PREVIOUSLY AND EXPRESSLY ACKNOWLEDGED IN WRITING BY SSI.



800-888-8909 • Fax 918-582-7510 • www.ssicm.com

For Purchase, contact SSI at the following locations:

TULSA OK (918)587-5567 ♦ OKLAHOMA CITY OK (405)524-9525 ♦ SPRINGDALE AR (479)751-3170 ♦ DALLAS TX (972)243-0676 ♦ DALLAS- RICHARDSON (972)234-1163 ♦ FT WORTH TX (817)647-1881
HOUSTON TX- SABINE, (713)862-3900 ♦ HOUSTON- BLAYLOCK, (713)460-8800 ♦ AUSTIN TX (512)326-1156 ♦ SAN ANTONIO TX (210)930-6360 ♦ EL PASO TX (915)591-6800 ♦ MCALLEN TX (956)782-1341
BATON ROUGE LA (225)620-0950 ♦ NEW ORLEANS LA (504)539-3102 ♦ KANSAS CITY MO (816)561-1617 ♦ ST LOUIS MO (310)410-6800

We know you have a choice, thank you for choosing SSI.